

RIVITAL REVITALISING WATER-BASED TREATMENT

Datasheet code MAX023956T

Rev. 02 of 05.12.2020 Page 1 of 2

Name	RIVITAL REVITALISING WATER-BASED TREATMENT
Description	Conditioner for varnished wood with cloth/brush application.
Main characteristics	<ul style="list-style-type: none">- Non-yellowing.- Good fullness and brightness.
CLASSIFICATION (UNI 8681)	A.4.C.0.A.0.AB Varnish for finishing layer, in water dispersion, mono-component, physical drying, gloss, alkyd.
VOC CLASSIFICATION VOC classification (Directive 2004/42/EC)	Impregnating varnishes for wood which form a film with a minimum thickness. EU Limit value of VOCs for TREATMENT' Water (cat. A/I): 130 g/L (2010). This product contains max. 130 g/L of VOCs.
APPLICATION CYCLE	RIVITAL WATER-BASED RIVITALIZING TREATMENT should be applied directly on the old varnish without sanding. It is suitable for all exposed woodwork, as long as it does not have a shiny mirror finish.
HELPFUL HINTS	Environmental and substrate conditions: The substrate must be dry, free of dust, grease, and any other polluting substances. Room temperature: min. +10°C / max. +35°C Ambient relative humidity < 75% Substrate temperature: min. +10°C / max. +35°C
Safety precautions	Close the container immediately after use. Store tightly closed, undiluted, away from heat, frost, and direct sunlight. Empty containers or containers with slight traces of dried residual product film should be disposed of according to local regulations. Safety information for the user can be found in the relevant safety data sheet.

RIVITAL REVITALISING WATER-BASED TREATMENT

Datasheet code MAX023956T

Rev. 02 of 05.12.2020 Page 2 of 2

Characteristics and other technical information	Method	Main data at 20°C and 60% Relative Humidity
Aspect and finish gloss	UNI 9389	Shiny Min. 60
Volumic mass	UNI 8910	1,000 – 1,040 g/ml
Viscosity ISO Ø 6, s	UNI 8356	13 – 20
Theoretical yield per coat	ISO 7254	18 – 20 m ² /litre
Recommended dry thickness	ASTM D 1186	30 – 35 microns per coat
Flash point °C	UNI 8909	Not flammable
Shelf life (in a cool and dry place)	UNI 10154	At least 24 months
Dry-to-touch		1 hour
Dry-in-depth		5 – 6 hours
Over-varnishability		5 – 6 hours
Indoors/outdoors		Yes\ yes
Cleaning the instruments		Water
Colours		Colourless
Binder		Alkyd
Diluent		Water
Brush/cloth application % in volume		Ready to use

This information is supplied on the basis of our best technical and applicative knowledge, but every recommendation and suggestion given is without any guarantee since the conditions of use are not under our direct control. In case of doubt it is always advisable to conduct some preliminary tests and/or ask for the intervention of our technicians.



Monday -Thursday 8:30-17:30
Friday 8:30-15:30



Cromology Italia S.p.a. Registered office: Via IV Novembre 4

55016 Porcari (LU) ITALY
Tel. 199119955 Fax 199119977

www.maxmeyer.it, E-mail: info@maxmeyer.it