

Name	TOPGLASS FLATTING ACQUA
Description	Water-based high-gloss paint for wood.
Main features	<ul style="list-style-type: none">- Non-yellowing.- Good fullness and gloss finishing.
Tinting System	TOPGLASS FLATTING ACQUA can be coloured with our tinting system.
Classification (UNI 8681)	A.4.C.0.A.0.FA Top coating paint, in water dispersion, single-component, physically drying, glossy, acrylic.
VOC Classification (Directive 2004/42/EC)	Interior/exterior trim varnishes and woodstains, including opaque woodstains. EU limit value for TOPGLASS FLATTING ACQUA (cat. A/e): 130 g/L (2010). TOPGLASS FLATTING ACQUA contains max 130 g/L VOC.
Application cycle	NEW WOOD: Apply a first coat of Active Impregnante all'Acqua over dry, clean and seasoned wood. After 6-8 hours sandpaper with medium-grain abrasive paper and apply two or more coats of product, allowing 6-8 hours' drying between coats. PAINTED WOOD: Remove any loose paintwork with a scraper. Wash the whole surface with a detergent, rinse well and allow to dry. Touch up the parts where the paint has come off with TOPGLASS FLATTING ACQUA thinned 20%. Apply two or more coats of product allowing 6-8 hours' drying between coats.
Practical advice	Environmental and surface conditions: The surface must be dry and free from dust, grease and other pollutants. Room temperature: min. 10°C / max. 35°C Relative humidity: <75% Surface temperature: min. 10°C / max. 35°C Tool cleaner: Clean used tool eliminating the paint as much as possible using the tin edge as a fulcrum. Do not use running water. Plunge in a minimum quantity water the used tools.
Safety data	<ul style="list-style-type: none">• Keep the tin tightly closed and protected from frost in a cool place away from heat sources.• User's safety information is contained in the related safety sheet.• Empty containers, or with traces of dried product film, must be disposed of according to local regulations.
Tender item	Application of TOPGLASS FLATTING ACQUA with an average consumption of _____ l per sq. m, to be applied in two coats at a cost of € _____ per sq. m, including materials and labour, and excluding scaffoldings and surface dressing.

Specifications and other technical information	Method	Main data at 20°C and 60% relative humidity
Coat finish and aspect gloss	UNI 9389	Glossy 80 ÷ 90
Density g/ml	UNI 8910	1,000 ÷ 1,060
Viscosity ISO Ø 6, s	UNI 8356	65 ÷ 75
Calculated spreading rate sq. m/l	ISO 7254	18 ÷ 20
Recommended dry film thickness microns per coat	ASTM D 1186)	30 ÷ 35
Flash point °C	UNI 8909	Not flammable
Shelf life (in cool and dry place)	UNI 10154	At least 36 months
Touch dry hrs		1
Hard dry hrs		5 ÷ 6
Dry to recoat hrs		5 ÷ 6
Exteriors/Interiors		YES/YES
Colours		Colourless
Binder		Acrylic
Thinner		Water
Roller application volume %		5%
Brush application volume %		Max. 5%
Spray and air application volume %		10 ÷ 15%

The above information is based on our best technical and practical knowledge. However, since the actual conditions in which the product is used are beyond our direct control, we provide no guarantee as to the effectiveness of the recommendations and suggestions contained herein. If in doubt, it is advisable to conduct preliminary tests and/or call our Technical Service.

Servizio Clienti



Lunedì – Venerdì 8:30-17:30



Cromology Italia S.p.a.: sede legale Via IV Novembre, 4
55016 Porcari (LU) ITALY
Tel. 199 119955 Fax 199 119977
www.maxmeyer.it, E-mail: info@maxmeyer.it