
ERAMETAL



www.vieropaints.com

info@vieropaints.it

Product data sheet: VID455161T

Rev. 03 dated 09/03/2021

Name	ERAMETAL
Description	Smooth finish for metallic effects
Product characteristics	ERAMETAL is an enamel for interiors, formulated with selected metallic pigments that allow for multiple decorative solutions depending on the tool and the technique employed.
VOC Classification (Volatile organic compounds) Directive 2004/42/EC	Glossy paints for interior walls and ceilings. EU limit value for ERAMETAL (Cat. A/I): 200g/L (2010). ERAMETAL contains no more than 200 g/L of VOC.
Produced in	MADE IN ITALY
Main application tools	Roller, brush, pad, spatula
Application method	The surface must be uniform, matured, absorbent and free of patches or plastic finishes. In case, clean the surface well, removing all traces of previous paint and/or plaster, dirt, grease etc., by brushing, sanding or with cleaning equipment. Apply a coat of PRYMER ACQ in case of chalky surfaces. Render, if necessary, with STUCCO FONDO and let it cure. Apply 1 or 2 coats of product.
Practical tips	<p>The base coat should be set, clean and free from any chipping, peeling and/or dampness. New plasters should be left to age for at least 4-5 weeks to allow for complete carbonation.</p> <p>Environmental conditions -> temperature: min. + 5 °C/max. + 35 °C, relative humidity: < 75%. Primer conditions -> temperature: min. + 5 °C/max. + 35 °C, humidity: < 10 with respect to relative humidity.</p> <p>Shake the product before use or, if it is very dense, use a spatula or a mixing drill to achieve a workable consistency.</p> <p>It is recommended that the colour of the completely dried product be checked before application.</p> <p>Do not apply the product on surfaces exposed to direct sunlight or in the presence of strong drafts.</p> <p>Do not rework on the same surface.</p> <p>Do not interrupt application in the middle of a wall.</p> <p>The product may not be stored for more than 48 hours after dilution.</p> <p>Rinse used tools with water immediately after use.</p> <p>Keep the paint can sealed and away from freezing temperatures and sunlight.</p>
Safety precautions	Safety information for users is contained in the relative safety data sheet. Empty containers or containers with traces of dried product film should be disposed of according to local regulations.

FOR PROFESSIONAL USE ONLY

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

ERAMETAL



www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455161T
Rev. 03 dated 09/03/2021

TECHNICAL/REGULATORY INFORMATION	APPLICABLE REGULATION	INFO AT 20 °C AND 60% HUMIDITY
Appearance in the can Finish appearance		Liquid Satin
Density g/ml	UNI 8910	1,13 ÷ 1,23
Brookfield Viscosity cPs	ASTM D 2196	9000 ÷ 17000
Natural spread (m ² /L) per coat	ISO 7254	16
Natural spread rate of coat for spatula effect (m ² /L)		7-9
Flash point °C	UNI 8909	Non-flammable
Shelf life (in a cool and dry place)	UNI 10154.	At least 12 months
Dry to touch Hours (h)		2 ÷ 3
Hard dry Hours (h)		18 ÷ 24
Overcoating Hours (h)		24
Application places		Interiors
Base + achievable colours		Gold, silver + Erametal colour collection
Binder		Acrylic
Tool cleaning		Water
Roll and brush dilution% by volume		Ready to use

FOR PROFESSIONAL USE ONLY

Toll Free Number: 800.219.420 (Italy)
International assistance: +39.0583.2424 (from other countries)

Mon - Fri [8:00 am/1:00 pm - 2:00 pm/5:30 pm]

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

ERAMETAL

Product data sheet: VID455161T
Rev. 03 dated 09/03/2021



CROMOLOGY
Italia

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =
= ISO 14001 =
= OHSAS 18001 =

Viero

www.vieropaints.com
info@vieropaints.it

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424